

## TECHNICAL SHEET



Article:	<b>B0175 HARLEM</b>
Norm:	<b>EN ISO 20345:2012</b>
Safety Class:	<b>S1 P SRC</b>
Footwear height:	<b>Mod. A, H 91 mm (&lt;113 mm, Rif. EN 20345-5.2.2)</b>
Width:	<b>11</b>
Construction:	<b>STROBEL; PU SOLE</b>
Cleaning and maintenance:	Use only soft brushes and water. Do not use substances such as alcohol, thinners, gasoline, oil or any other chemicals. Keep the footwear, dry and clean, in a proper place at room temperature.
Suggested fields:	<b>Mechanics, construction finishes, light industry, logistics.</b>

Entire footwear: protections					
Component	Description	Value	Norm Requirements	EN 20345	
Steel	Impact resistance(200 J)				
Toe-cap	• Free height after impact	15,5 mm	≥ 14 mm	5.3.2.3	
	Compression resistance (15 kN)				
	• Free height after compression	15 mm	≥ 14 mm	5.3.2.4	
Sole (SRC)	Slip resistance				
	• SRA – Sole (entire sole)	0,42	≥ 0,32	5.3.5.4	
	• SRA – Heel (Angle of 7°)	0,38	≥ 0,28	5.3.5.4	
	• SRB – Sole (entire sole)	0,21	≥ 0,18	5.3.5.4	
	• SRB – Heel (Angle of 7°)	0,19	≥ 0,13	5.3.5.4	
Fresh'n Flex (P)	Puncture resistance	No perforation	≥ 1100 N	6.2.1.1.2	
Footbed (A)	Antistatic properties	• Electrical resistance			
			dry 7,61 x 10 <sup>8</sup> Ω	≥ 10 <sup>5</sup> Ω , ≤ 10 <sup>9</sup> Ω	6.2.2.2
		humid 4,93 x 10 <sup>8</sup> Ω	≥ 10 <sup>5</sup> Ω , ≤ 10 <sup>9</sup> Ω	6.2.2.2	
Sole/Upper	Thermal insulation				
	Heat (HI)	Insole temperature increase	N/A	≤ 22°C	6.2.3.1
	Cold (CI)	Insole temperature decrease	N/A	≤ 10°C	6.2.3.2
Heel (E)	Shock-absorption in the heel region	25 J	≥ 20 J	6.2.4	
(WR)	Water resistance (Water absorption)	N/A	≤ 3 cm <sup>2</sup>	6.2.5	
(M)	Metatarsal protection	N/A	≥ 40 mm	6.2.6	

Upper				
Component	Description	Value	Norm Requirements	EN 20345
Suede leather	Tear resistance	188 N	≥60 N	5.4.3
	Traction resistance	19	≥ 15 N/mm <sup>2</sup>	5.4.4
	Water steam permeability	4,2mg/cm <sup>2</sup> h	≥0.8 mg/cm <sup>2</sup> h	5.4.6
	pH value	4,05	≥ 3,2	5.4.7
	Chromium VI	Not detected	No detectable	5.4.9
	Water passed	N/A	≤ 0.2 g	6.3
	Water absorption	N/A	≤ 30%	6.3

Lining				
Component	Description	Value	Norm Requirements	EN 20345
3D Hi Tech Fabric	Tear resistance	47 N	≥ 15 N	5.5.1
	Abrasion resistance	• Dry : the surface shows no holes	No holes till 51.200 cycles	5.5.2
		• humid: the surface shows no holes	No holes till 25.600 cycles	5.5.2
	Water steam release	21,1 mg/cm <sup>2</sup> h	≥ 2,0 mg/cm <sup>2</sup> h	5.5.3
	pH value	N/A	No detectable	5.5.4
	Chromium VI	N/A	No detectable	5.5.5

Insole				
Component	Description	Value	Norm Requirements	EN 20345
Fresh n' flex	Thickness	3,7 mm	≥ 2,0 mm	5.7.1
	pH value	N/A	No detectable	5.7.2
	Water absorption	86 mg/cm <sup>2</sup>	≥ 70 mg/cm <sup>2</sup>	5.7.3
	Water release	94 %	≥ 80 %	5.7.3
	Abrasion resistance (after 400 cycles)	No damage	Damage ≤ to norms reference	5.7.4.1
	Chromium VI	N/A	No detectable	5.7.5

Removable footbed				
Component	Description	Value	Norm Requirements	EN 20345
Anatomical, breathable, textile and expanded polymeric material	Thickness	3,5±0,5 mm	N/A	5.7.1
	pH value	N/A	No detectable	5.7.2
	Water absorption	Permeable	Permeable or ≥ 70mg/cm <sup>2</sup>	5.7.3
	Water release	Permeable	Permeable or ≥ 80%	5.7.3
	Abrasion resistance	No damage	Dry No holes till 25.600 cycles Humid no holes till 12.800 cycles	5.7.4.2
	Chromium VI	N/A	No detectable	5.7.5

Component	Description	Value	Norm Requirements	EN 20345
Dry'n Air Gel	Thickness	3,5±0,5 mm	N/A	5.7.1
	pH value	N/A	No detectable	5.7.2
	Water absorption	Permeable	Permeable or ≥ 70mg/cm <sup>2</sup>	5.7.3
	Water release	Permeable	Permeable or ≥ 80%	5.7.3
	Abrasion resistance	No damage	Dry No holes till 25.600 cycles Humid no holes till 12.800 cycles	5.7.4.2
	Chromium VI	N/A	No detectable	5.7.5

Sole					
Component	Description	Value	Norm Requirements	EN 20345	
PU Monodensity Sole	Sole thickness without profiles	9 mm	≥ 4 mm	5.8.1.1	
	Profiles height	4 mm	≥ 2,5 mm	5.8.1.3	
	Tear resistance	6,1 kN/m	≥ 8 kN/m	5.8.2	
	Abrasion resistance	• relative volume loss	173 mm <sup>3</sup>	≤ 250 mm <sup>3</sup>	5.8.3
		• Notches increase after 30.000 cycles	1,5 mm	≤ 4 mm	5.8.4

Hydrolysis			
• Notches increase after 150.00 cycles	2,5 mm	≤ 6 mm	5.8.5
Outsole – insole detachment	N/A	≥ 4 N/mm; (*) ≥ 3 N/mm with sole ripping	5.8.6
(HRO) Contact heat resistance (300°C)	N/A	No damage (melting, breaking)	6.4.1
(FO) Fuel resistance (volume changes)	0,1 %	≤ 12%	6.4.2

Date: 23/04/2019

Copy in accordance with the Italian sheet